

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 02-024192

(43)Date of publication of application : 26.01.1990

(51)Int.Cl.

B41M 5/38

(21)Application number : 63-174460

(71)Applicant : RICOH CO LTD

(22)Date of filing : 13.07.1988

(72)Inventor : KAMIMURA HIROYUKI
SUZUKI AKIRA
SHIMADA MASARU
MOCHIZUKI HIDEHIRO

(54) SUBLIMATE TYPE THERMAL TRANSFER MEDIUM

(57)Abstract:

PURPOSE: To obtain high recording density without decreasing transfer density even though printing is performed many times by establishing a dye migration preventive layer between a base material and a dye supply layer.

CONSTITUTION: For a transfer medium, a dye migration preventive layer 2 is provided onto a surface of a base material 1, and a dye supply layer 3 composed of a thermal sublimable dye and an organic binding agent is established thereon. Further, a transfer contributive layer 4 composed of the thermal sublimable dye and the organic binding agent is laminated thereon. The thermal sublimable dye from the dye supply 3 is dislocated by heating with a thermal head 6 to a surface of an image receiving medium 5 via the transfer contributive layer 4 to be transferred by sublimation. Since the dye migration preventive layer 2 is provided in that case, no thermal sublimable dye is diffused to the base material 1 side. The thermal sublimable dye is effectively used for formation of an image, and the image of high density can be many times repetitively obtained.

